

System 4

Location

Decks

Description

Walkways, escape routes and lay down areas

Pre-qualification is required

| Product | DFT μm |
|---|-------------------|
| Hempadur 15590 (diluted) < 120°C ¹ | 20 |
| Hempadur Spray-Guard 35493 | 3000 |
| Total | 3020 |
| Hempadur Spray-Guard 35493 | 1500 |
| Hempadur Spray-Guard 35493 | 1500 |
| Total | 3000 |

Note¹ = The use of Hempadur 15590 is optional.

Note² = Coating systems pre-qualified according to NORSOK M-501 System 1 may be used for other deck areas with the addition of a non-skid aggregate (Hempel 67500). This note applies to all of the above systems.