

System 9

Location

Valves

Description

Bulk supplied carbon steel valves with operating temperatures up to 150°C/302°F

Pre-qualification is not required

Product	DFT μm
Hempadur 85671	150
Hempadur 85671	150
Total	300
Hempel's Galvosil 15700 ²	75
Hempadur 85671	160
Total	235
Hempel's Galvosil Fibre 15750 ²	75
Hempadur 85671	160
Total	235

Note¹ = For temperatures above 150°C thermally sprayed aluminium shall be used. This note applies to all of the above systems.

Note² = An alternative system if agreed with the purchaser may be 1 x 75 μm Zinc ethyl silicate and an epoxy tie coat in accordance with System 1. Final coating shall then be done after insulation. Hempel recommend that this is used for uninsulated items only.