

# Hempel's Aluxtra 71260

## Product characteristics

### Description

Hempel's Aluxtra is a high performance, self-polishing antifouling providing excellent protection all season. Especially suited for aluminium boats. Bright, clean colour make it a good choice for all below waterline areas including sterngear and propellers.

### Recommended use

For use as an antifouling for boats of glass fibre, wood, plywood, steel and aluminium. Ensure aluminium substrates are suitably primed.

### Features

- Excellent mechanical strength for superior crack resistance.

## Product safety

**Flash point** 34°C [93°F]

### VOC content

Legislation	Value
EU	396 g/L [3.30 lb/US gal]

VOC values may vary with shade, please consult the Safety Data Sheet, section 9.

### Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

## Product data

### Product code

71260

### Standard shade\* / code

White 10000

### Gloss

Semi-flat

### Volume solids

54 ± 2%

### Specific gravity

1.4 kg/L [12 lb/US gal]

### Reference dry film thickness

40 micron [1.6 mils]

## Surface preparation

### Cleanliness

- Remove salts, detergents, contaminants and marine growth by high pressure fresh water cleaning.
- Clean with Hempel's Pre-Clean.

### New build:

- Uncoated surface: Prime prepared surface with Hempel's Light Primer and apply a tiecoat of Hempel's Underwater Primer whilst the surface is still tacky.
- Uncoated surface: Prime prepared surface with Hempel's Premium Primer. Apply one coat of Hempel's Pro Tiecoat.

### Maintenance and Repair

- Existing old self-polishing or traditional antifouling: Remove loose matter and contaminants by high pressure fresh water cleaning.
- Existing old hard matrix antifouling or an unknown antifouling: High pressure fresh water clean, wet abrade, remove dust.
- Clean and dry the surface.
- If previous antifouling is in general bad condition, it is recommended to remove previous coats and prime before applying antifouling.
- If the condition of previous antifouling is poor, seal with 1 coat of Hempel's Underwater Primer or Hempel's Pro Tiecoat.

# Hempel's Aluxtra 71260

## Application

### Thinner

Hempel's Thinner 08080

### Cleaner

Hempel's Thinner 08080  
Hempel's Thinner 808 08081

### Application method

Tool	Thinning max vol.	Application parameters
Brush/Roller	5%	Not Applicable.
Airless spray	5%	Nozzle pressure: 150 bar [2200 psi] Nozzle orifice: 0.018-0.023"

The product can be applied by spray. Contact Hempel for more information. Spray data are indicative and subject to adjustment. Pressure is for a material temperature of 20°C [68°F].

### Film thickness

	Recommended
Dry film thickness	40 micron [1.6 mils]
Wet film thickness	75 micron [3 mils]
Theoretical spreading rate	14 m <sup>2</sup> /L [570 sq ft/US gal]

### Application conditions

- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.

### Relative Humidity:

- Relative humidity must be below 85% during application.

### Application remarks

- Copper containing antifouling must not have any electrical contact with aluminium hull and other aluminium components.
- Airless spray: Apply 1 coat of the product. (80 micron dry film thickness).
- Air spray / Brush or roller: Apply 2 coats of the Antifouling paint at 40 µm dry film thickness each.
- Wear protective gloves/clothing and eye/respiratory protection.

## Drying and overcoating

### Product compatibility

- Previous coat: Recommended products are: Hempel's Underwater Primer; Hempel's Light Primer; Hempel's Pro Tiecoat

### Drying time

Surface temperature		20°C [68°F]	10°C [50°F]	30°C [86°F]
Touch dry	min	15	30	9

Determined for dry film thickness 40 micron [1.6 mils] at standard conditions, see Hempel's Explanatory Notes for details. Time to immersion: Minimum: 24 Hours 20°C ; Maximum 6 months

### Overcoating

Hempel's specification supersedes any guidelines indicated in the overcoating table

Quality name		10°C [50°F]	20°C [68°F]	30°C [86°F]
		Immersion		
Hempel's Aluxtra 71260	Min	8 h	4 h	3 h
	Max	Ext	Ext	Ext

### Drying conditions

- To obtain the drying time stated, it is important to maintain sufficient ventilation during application, drying and curing.
- Condensation on the freshly applied coating should be avoided.

### Overcoating details

- No maximum overcoat interval, but after prolonged exposure to polluted atmosphere, remove accumulated contamination by high pressure fresh water cleaning and allow to dry before applying next coat.

# Hempel's Aluxtra 71260

## Storage

### Shelf life

Ambient temperature	25°C [77°F]
Product	60 months

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Always check the best before date or expiry date on the label.

### Storage conditions

- Product must be stored according to local legislation, at 5°C [41°F] without direct sunlight and protected from rain and snow.

## Additional documents

Additional information is available at the Hempel website [hempel.com](http://hempel.com) or at your local Hempel website:

- Explanatory Notes explaining the fields in this Product Data Sheet.
- Surface Preparation Guidelines.
- Application Guidelines for different application methods.

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at [www.hempel.com](http://www.hempel.com) (the "Additional documents"):

No.	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at <a href="http://www.hempel.com">www.hempel.com</a> and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at <a href="http://www.hempel.com">www.hempel.com</a>
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at <a href="http://www.hempel.com">www.hempel.com</a>

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from [www.hempel.com](http://www.hempel.com).

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.