Hempel's Speed-Dry Alkyd 43140

Product characteristics

Description
Hempel's Speed-Dry Alkyd 43140 is a very quick-drying anticorrosive primer/finish pigmented with zinc phosphate as anticorrosive inhibiting pigment. Hempel's Speed-Dry Alkyd 43140 is also available in a Micaceous Iron Oxide and aluminium pigmented version as shade 19760.
Complies with EU Directive 2004/42/EC, The Paints Directive on the limitation of volatile organic compounds: subcategory i.

Recommended use
As a single/double coat anticorrosive primer/finish for steel structures, general steel work and a multitude of applications for heavy and light steel industry, where quick drying properties are required. It is for general use, in exterior and interior steel surfaces. Suitable for protection of steel in mild to medium atmospheric corrosive environments.

Service temperature:
- Maximum, dry exposure only: 120°C [248°F].
- Minimum, recommended by Hempel for dry exposure: -50°C [-58°F].

Certificates / Approvals
- Reaction to fire tested (as part of a coating system with approved primer and topcoat) according to EN13501-1 B-s1, d0.

Features
- Very fast drying properties, perfect solution for in shop application
- Excellent overcoatability with itself or similar alkyds, with Hempathane and Hempadur. Good overcoatability with Hempalin and Hempatex
- Good results with most means of application including brush
- Good adhesion to steel
- Friendly for both user and environment, does not contain any lead and chromates

Product safety

Flash point 25°C [77°F]

VOC content

Legislation	Value
EU	443 g/L [3.70 lb/US gal]
US (coatings)	443 g/L [3.70 lb/US gal]
US (regulatory)	443 g/L [3.70 lb/US gal]
China	443 g/L [3.70 lb/US gal]

According to specific legislation, see details in the Explanatory Notes available at Hempel website, hempel.com or at your local Hempel website. VOC values may vary with shade, please consult the Safety Data Sheet, section 9. [a]EU Directive 2004/42/CE.

Handling
Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

Product data

Product code: 43140

Standard shade / code: Light grey 11150 *

Wide range of colours is available via Hempel's tinting system.

Gloss: Flat

Volume solids: 49 ± 2%

Specific gravity: 1.4 kg/L [12 lb/US gal]

Reference dry film thickness: 60 micron [2.4 mils]

Aluminium shade / code: Aluminium grey 19001

Gloss: Please consult Hempel's Guideline on aluminium pigmented coatings.

Volume solids: 43 ± 2%

Specific gravity: 1.3 kg/L [11 lb/US gal]

* The natural tendency of Alkyds to discolour is also reflected in this product. Discoloration can be accelerated by inadequate ventilation, exposure to chemicals, elevated temperatures and low light conditions.

Hempel's Speed-Dry Alkyd 43140

Reference dry film thickness: 60 micron [2.4 mils]

Surface preparation

Cleanliness
- Remove oil, grease and other contaminants by suitable detergent cleaning.
- Remove salts, detergents and other contaminants by high pressure fresh water cleaning.

New build:
- All damage of shopprimer and contamination from storage and fabrication should be thoroughly mechanically/chemically cleaned prior to final painting.
- Abrasive blasting to min. Sa 2½ (ISO 8501-1) / SP 10 (SSPC) / NACE No.2.
- Remove dust, blast media and loose materials.
- The surface must be dry and clean prior to application.

Maintenance and Repair
- Spot abrasive blasting to min. PSa 2 (ISO 8501-2) / SP 6 (SSPC).
- Minor areas can be cleaned by power tool to St 3 provided the surface is roughened and not polished.
- Remove dust, blast media and loose materials.

Consult Hempel's separate Surface Preparation Guidelines for more details.

Application

Mixing ratio
Stir well before use.

Thinner
Hempel's Thinner 08080

Cleaner
Hempel's Thinner 08080

Application method

Tool	Thinning max vol.	Application parameters
Airless spray	5%	Nozzle pressure: 200 bar [2900 psi] Nozzle orifice: 0.015-0.021"
Brush	5%	-
Roller	5%	-

If brush or roller application is used, more coats will be necessary to achieve the specified dry film thickness. Spray data are indicative and subject to adjustment. Pressure is for a material temperature of 20°C [68°F].

Film thickness

Specification range	Low	High	Recommended
Dry film thickness	40 micron [1.6 mils]	120 micron [4.8 mils]	60 micron [2.4 mils]
Wet film thickness	81 micron [3.3 mils]	244 micron [9.8 mils]	122 micron [4.9 mils]
Theoretical spreading rate	12 m²/L [489 sq ft/US gal]	4.1 m²/L [167 sq ft/US gal]	8.2 m²/L [334 sq ft/US gal]

Product may be specified in another film thickness than indicated depending on purpose and area of use. This will alter spreading rate, drying and curing time and overcoating interval. For best performance, avoid excessive film thickness.

Application conditions
- Surface temperature must be above 5°C [41°F] during application and curing.
- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.

Relative Humidity:
- Relative humidity must be below 90% during curing.
- Relative humidity must be below 90% during application.

Drying and overcoating

Product compatibility
- Previous coat: According to Hempel's Specification.
- Subsequent coat: According to Hempel's Specification.

Hempel's Speed-Dry Alkyd 43140

Drying time

Surface temperature		20°C [68°F]
Surface dry	min	15
Hard dry	min	60

Determined for dry film thickness 60 micron [2.4 mils] at standard conditions, see Hempel's Explanatory Notes for details.

Overcoating

Hempel's specification supersedes any guidelines indicated in the overcoating table

Quality name		20°C [68°F]
Atmospheric medium		
Hempatex Enamel 56360	Min Max	15 min 24 h
Hempathane HS 55610	Min Max	30 min Ext*
HempaQuick Enamel	Min Max	15 min Ext*
Hempel's Speed-Dry Alkyd 43140	Min Max	15 min Ext*

Ext*: Depending on the actual exposure conditions, the coated surface is overcoatable for an extended period of time. Contact your local Hempel representative for advice.
Overcoating times are indicative for products of the same generic chemistry when applied at the recommended DFT.
Consult Hempel's specification for more information.

Drying conditions

- To obtain the drying time stated, it is important to maintain sufficient ventilation during application, drying and curing.

Overcoating details

- If the maximum overcoating interval is exceeded, roughening of the surface is necessary to ensure intercoat adhesion.
- The surface must be clean before overcoating.

Other remarks

- Hempel's Specification supersedes any recommendations given in the Product Data Sheets.

Storage

Shelf life

Ambient temperature	25°C [77°F]
Product	36 months

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Storage at elevated temperatures may reduce shelf life. The shelf life printed on product labels is based on regional climate conditions. For advice, please consult Hempel.

Storage conditions

- The product must be stored in accordance with Safety Data Sheet, label and local regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Carbon Footprint

Dry film thickness	1 µm	1 mil
GWP (Global Warming Potential)	8.3 g CO_2e/m^2	0.043 lb CO_2e/ft^2

The carbon footprint is for 1 square meter / square foot of surface area with a dry film thickness of 1 micron / mil.

The scope includes raw materials, in-bound transport to the Hempel factory, Hempel manufacturing processes, and any Volatile Organic Compounds emitted during and after the application of the product.

It is calculated based on the standard shade defined in this PDS. Values may vary with shade.

Hempel's Speed-Dry Alkyd 43140

Additional documents

Additional information is available at the Knowledge Center:
https://www.hempel.com/knowledge-center
. The documents below can be found in the Technical Guidelines section:
https://www.hempel.com/knowledge-center/technical-guidelines
or at the Hempel website.

- Explanatory Notes for Product Data Sheet.
- Application methods.
- General Application Guidelines

This Product Data Sheet ("**PDS**") relates to the supplied product ("**Product**") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at www.hempel.com (the "**Additional documents**"):

No.	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at www.hempel.com and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at www.hempel.com
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at www.hempel.com

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from www.hempel.com.

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.