

# Hempaxane Light

## Product characteristics

### Description

Hempaxane Light 55030 is a two-component, high-solids, glossy, polysiloxane enamel with outstanding gloss and colour retention.

### Recommended use

Hempaxane Light is recommended as an isocyanate-free glossy decorative and protective finishing coat for structures in severely corrosive atmospheric environment.

### Service temperature:

- Maximum, dry exposure only: 120°C [248°F].

### Certificates / Approvals

- Third-party verified, product-specific Environmental Product Declaration (Type III EPD, ISO 14025, EN 15804)
- Meets requirements to NORSOK M-501 when used as part of a predefined paint system. Edition 6, System 1. Edition 7, System 1A, 1B.

## Product safety

**Flash point** 33°C [91°F]

### VOC content mixed product

Legislation	Value
EU	206 g/L [1.72 lb/US gal]
US (coatings)	204 g/L [1.70 lb/US gal]
US (regulatory)	205 g/L [1.71 lb/US gal]
China	206 g/L [1.72 lb/US gal]

According to specific legislation, see details in the Explanatory Notes available at Hempel website, [hempel.com](http://hempel.com) or at your local Hempel website. VOC values may vary with shade, please consult the Safety Data Sheet, section 9.

### Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

## Product data

### Product code

55030

### Product components

Base 55039  
Curing Agent 98000

### Standard shade / code

Agate Grey 17380 \*  
Light grey 17380

Wide range of colours is available via Hempel's tinting system.

### Gloss

Glossy

### Volume solids

83 ± 2%

### Specific gravity

1.4 kg/L [12 lb/US gal]

### Reference dry film thickness

75 micron [3.0 mils]

# Hempaxane Light

## Surface preparation

### Cleanliness

- According to Hempel's Specification.

### New build:

- According to Hempel's Specification.

### Maintenance and Repair

- According to Hempel's Specification.

Consult Hempel's separate Surface Preparation Guidelines for more details.

## Application

### Mixing ratio

Base 55039 : Curing Agent 98000  
(56 : 44 by volume)

Stir well before use.

### Thinner

Hempel's Thinner 08080

### Cleaner

Hempel's Tool Cleaner 99610

### Pot life

<b>Product temperature</b>	<b>20°C</b> [68°F]
----------------------------	-----------------------

Pot life	4 hours
----------	---------

## Application method

Tool	Thinning max vol.	Application parameters
Airless spray	10%	Nozzle pressure: 100-125 bar [1500 psi] Nozzle orifice: 0.017-0.021"
Brush	5%	Not Applicable.
Roller	5%	Not Applicable.

If brush or roller application is used, more coats will be necessary to achieve the specified dry film thickness. Spray data are indicative and subject to adjustment. Pressure is for a material temperature of 20°C [68°F].

## Film thickness

Specification range	Low	High	Recommended
Dry film thickness	50 micron [2.0 mils]	100 micron [4.0 mils]	75 micron [3.0 mils]
Wet film thickness	60 micron [2.4 mils]	120 micron [4.8 mils]	90 micron [3.6 mils]
Theoretical spreading rate	17 m <sup>2</sup> /L [693 sq ft/US gal]	8.3 m <sup>2</sup> /L [338 sq ft/US gal]	11 m <sup>2</sup> /L [448 sq ft/US gal]

Product may be specified in another film thickness than indicated depending on purpose and area of use. This will alter spreading rate, drying and curing time and overcoating interval. For best performance, avoid excessive film thickness.

## Application conditions

- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.
- Surface temperature must be above 0°C [32°F] during application and curing.

## Relative Humidity:

- Relative humidity must be above 30% during curing.
- Relative humidity must be above 30% during application.

## Application remarks

- Two coats of the topcoat may be necessary to obtain full hiding power.

# Hempaxane Light

## Drying and overcoating

### Product compatibility

- Previous coat: None or according to Hempel's specification. Recommended products are: Hempel's Galvosil, Hempadur
- Subsequent coat: None.

### Drying time

Surface temperature		20°C [68°F]
Touch dry	hours	2½
Hard dry	hours	5½

Determined for dry film thickness 75 micron [3.0 mils] at standard conditions, see Hempel's Explanatory Notes for details.

### Overcoating

Hempel's specification supersedes any guidelines indicated in the overcoating table

Quality name	Atmospheric medium				
	0°C [32°F]	10°C [50°F]	20°C [68°F]	30°C [86°F]	
Hempaxane Light	Min	12 h	12 h	6 h	3 h
	Max	Ext*	Ext*	Ext*	Ext*

Ext\*: Depending on the actual exposure conditions, the coated surface is overcoatable for an extended period of time. Contact your local Hempel representative for advice.

Consult Hempel's specification for more information.

### Drying conditions

- To obtain the drying time stated, it is important to maintain sufficient ventilation during application, drying and curing.
- Condensation on the freshly applied coating should be avoided.

### Overcoating details

- If the maximum overcoating interval is exceeded, roughening of the surface is necessary to ensure intercoat adhesion.
- The surface must be dry and clean prior to application.

### Other remarks

- Hempel's Specification supersedes any recommendations given in the Product Data Sheets.

## Storage

### Shelf life

Ambient temperature	25°C [77°F]
Base	36 months
Curing Agent	18 months

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Storage at elevated temperatures may reduce shelf life. For advice, please consult Hempel.

### Storage conditions

- The curing agent is sensitive to moisture. Store in a dry place and keep the can tightly closed until use.
- The product must be stored in accordance with Safety Data Sheet, label and local regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

## Carbon Footprint

Dry film thickness	1 µm	1 mil
GWP (Global Warming Potential)	11.1 g CO <sub>2</sub> e/m <sup>2</sup>	0.058 lb CO <sub>2</sub> e/ft <sup>2</sup>

The carbon footprint is for 1 square meter / square foot of surface area with a dry film thickness of 1 micron / mil.

The scope includes raw materials, in-bound transport to the Hempel factory, Hempel manufacturing processes, and any Volatile Organic Compounds emitted during and after the application of the product.

It is calculated based on the standard shade defined in this PDS. Values may vary with shade.

# Hempaxane Light

## Additional documents

Additional information is available at the Hempel website <https://www.hempel.com/service-and-support/technical-guidelines> or at your local Hempel website:

- Explanatory Notes for Product Data Sheet.
- Application methods.
- General Application Guidelines

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at [www.hempel.com](http://www.hempel.com) (the "Additional documents"):

No.	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at <a href="http://www.hempel.com">www.hempel.com</a> and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at <a href="http://www.hempel.com">www.hempel.com</a>
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at <a href="http://www.hempel.com">www.hempel.com</a>

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from [www.hempel.com](http://www.hempel.com).

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.