

Hempel's Non-Slip Deck Coating

Product characteristics

Description

Hempel's Non-Slip Deck Coating is a quick-drying, acrylic, semi-gloss topcoat containing fine granules for an anti-slip finish. Durable with good resistance to weathering and abrasion.

Recommended use

For use on glass fibre, wood and steel. For interior and exterior use above the waterline.

Features

- Contains granules for a non-slip finish.

Product safety

Flash point 26°C [79°F]

VOC content

Legislation	Value
EU	477 g/L [3.98 lb/US gal]

VOC values may vary with shade, please consult the Safety Data Sheet, section 9.

Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

Product data

Product code

56251

Standard shade / code

White 10000 *

Gloss

Flat

Volume solids

46 ± 2%

Specific gravity

1.3 kg/L [11 lb/US gal]

Reference dry film thickness

50 micron [2.0 mils]

Surface preparation

Cleanliness

- Remove oil, grease and other contaminants by suitable detergent cleaning.

Application

Thinner

Hempel's Thinner 808 08081

Cleaner

Hempel's Thinner 808 08081

Hempel's Non-Slip Deck Coating

Application method

Tool	Thinning max vol.
Roller	5%
Brush	5%
Paint pad	5%

Keep thinning at an absolute minimum.

Film thickness

	Recommended
Dry film thickness	50 micron [2.0 mils]
Wet film thickness	109 micron [4.4 mils]
Theoretical spreading rate	9.2 m ² /L [375 sq ft/US gal]

For best performance, avoid excessive film thickness.

Application conditions

- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.

Relative Humidity:

- Relative humidity must be below 85% during drying and curing.

Application remarks

- Thinning of the topcoat may be required to ensure proper film formation. Thinning is limited to max. 5%.
- Stir well before use.

Drying and overcoating

Product compatibility

- Previous coat: Recommended products are: Hempel's Primer Undercoat ; Hempel's Light Primer
- Subsequent coat: None.

Drying time

Surface temperature		20°C [68°F]	10°C [50°F]
Touch dry	hours	2	4
Ready to sand	hours	3	-

Determined for dry film thickness 50 micron [2.0 mils] at standard conditions, see Hempel's Explanatory Notes for details. Any masking tape used during paint application should be removed while the paint is still in the wet condition.

Overcoating

Hempel's specification supersedes any guidelines indicated in the overcoating table

Quality name		10°C [50°F]	20°C [68°F]
Atmospheric medium			
Hempel's Non-Slip Deck Coating	Min	6 h	3 h
	Max	6 d	72 h

Drying conditions

- To obtain the drying time stated, it is important to maintain sufficient ventilation during application, drying and curing.
- Condensation on the freshly applied coating should be avoided.

Overcoating details

- If the maximum overcoating interval is exceeded, roughening of the surface is necessary to ensure intercoat adhesion.

Other remarks

- The surface must be clean before overcoating.
- Petrol, diesel, oil or acetone spills should not be allowed to pool. These products contain solvents which can damage the paint surface. Clean up spills using a suitable boat shampoo.

Hempel's Non-Slip Deck Coating

Storage

Shelf life

Ambient temperature	25°C [77°F]
Product	60 months

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Storage at elevated temperatures may reduce shelf life. For advice, please consult Hempel.

Storage conditions

- Product must be stored according to local legislation, at minimum 5°C [41°F], without direct sunlight and protected from rain and snow.

Carbon Footprint

Dry film thickness	1 µm	1 mil
GWP (Global Warming Potential)	10.1 g CO₂e/m²	0.053 lb CO₂e/ft²

The carbon footprint is for 1 square meter / square foot of surface area with a dry film thickness of 1 micron / mil.

The scope includes raw materials, in-bound transport to the Hempel factory, Hempel manufacturing processes, and any Volatile Organic Compounds emitted during and after the application of the product.

It is calculated based on the standard shade defined in this PDS. Values may vary with shade.

Additional documents

Additional information is available at the Hempel website <https://www.hempel.com/service-and-support/technical-guidelines> or at your local Hempel website:

- Explanatory Notes for Product Data Sheet.
- Application methods.
- Further information: Hempel Yacht Paint Manual and hempelyacht.com

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at www.hempel.com (the "Additional documents"):

No.	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at www.hempel.com and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at www.hempel.com
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at www.hempel.com

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from www.hempel.com.

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.