

# Hempalin Undercoat

# **Product characteristics**

#### Description

Hempalin Undercoat 42460 is a fairly quick-drying alkyd paint.

#### Recommended use

As a general purpose undercoating in alkyd paint systems on exterior and interior steelwork, wood, plaster, etc. in mildly to moderately corrosive environment.

## Service temperature:

- Maximum, dry exposure only: 120°C [248°F].

# **Product safety**

Flash point 38°C [100°F]

#### **VOC** content

Legislation	Value
EU	377 g/L [3.15 lb/US gal]
US (coatings)	377 g/L [3.15 lb/US gal]
US (regulatory)	377 g/L [3.15 lb/US gal]
China	377 g/L [3.15 lb/US gal]

According to specific legislation, see details in the Explanatory Notes available at Hempel website, hempel.com or at your local Hempel website.

#### Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

# Product data

#### **Product code**

42460

#### Standard shade / code

White 10000

#### **Gloss**

Flat

#### Volume solids

52 ± 2%

### Specific gravity

1.5 kg/L [12 lb/US gal]

### Reference dry film thickness

40 micron [1.6 mils]

# Surface preparation

### Cleanliness

- Remove oil, grease and other contaminants by suitable detergent cleaning.
- Remove salts, detergents and other contaminants by high pressure fresh water cleaning.

#### New build:

- All damage of shopprimer and contamination from storage and fabrication should be thoroughly mechanically/chemically cleaned prior to final painting.
- Abrasive blasting to min. Sa 21/2 (ISO 8501-1) / SP 10 (SSPC).
- Remove dust, blast media and loose materials.

# Maintenance and Repair

- Spot abrasive blasting to min. PSa 2 (ISO 8501-2) / SP 6 (SSPC).
- Minor areas can be cleaned by power tool to St 3 provided the surface is roughened and not polished.
- Remove dust, blast media and loose materials.

Consult Hempel's separate Surface Preparation Guidelines for more details.



# Hempalin Undercoat

# **Application**

#### Mixing ratio

Stir well before use.

#### Thinne

Hempel's Thinner 08230

#### Cleaner

Hempel's Thinner 08230

#### Application method

Tool	Application parameters	
Airless spray	Nozzle pressure: 150 bar [2200 psi] Nozzle orifice: 0.015-0.018"	
Air spray	Not Applicable.	
Brush	Not Applicable.	

If brush or roller application is used, more coats will be necessary to achieve the specified dry film thickness. Spray data are indicative and subject to adjustment. Pressure is for a material temperature of  $20^{\circ}$ C [68°F].

#### Film thickness

Specification range Low		High	Recommended	
Dry film thickness	30 micron	40 micron	40 micron	
	[1.2 mils]	[1.6 mils]	[1.6 mils]	
Wet film thickness	58 micron	77 micron	77 micron	
	[2.3 mils]	[3.1 mils]	[3.1 mils]	
Theoretical spreading 17 m²/L [693 sq ft/US gal]		13 m²/L [530 sq ft/US gal]	13 m²/L [530 sq ft/US gal]	

Product may be specified in another film thickness than indicated depending on purpose and area of use. This will alter spreading rate, drying and curing time and overcoating interval. For best performance, avoid excessive film thickness

## **Application conditions**

- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.
- Surface temperature must be above 5°C [41°F] during application and curing.

#### **Relative Humidity:**

- Relative humidity must be below 90% during drying and curing.

# Drying and overcoating

#### **Product compatibility**

- Previous coat: According to Hempel's Specification.
- Subsequent coat: According to Hempel's Specification.

#### **Drying time**

Surface temperature		<b>20°C</b> [68°F]
Touch dry	hours	4

Determined for dry film thickness 40 micron [1.6 mils] at standard conditions, see Hempel's Explanatory Notes for details.

## Overcoating details

- If the maximum overcoating interval is exceeded, roughening of the surface is necessary to ensure intercoat adhesion.
- The surface must be dry and clean prior to application.

## Other remarks

- Hempel's Specification supersedes any recommendations given in the Product Data Sheets.

# Storage

## Shelf life

Ambient	<b>25°C</b>
temperature	[77°F]
Product	60 months

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Storage at elevated temperatures may reduce shelf life. For advice, please consult Hempel.



# Hempalin Undercoat

#### Storage conditions

- The product must be stored in accordance with Safety Data Sheet, label and local regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

# **Carbon Footprint**

Dry film thickness	1 µm	1 mil
GWP (Global Warming Potential)	6.5 g CO₂e/m²	0.034 lb CO2e/ft <sup>2</sup>

The carbon footprint is for 1 square meter / square foot of surface area with a dry film thickness of 1 micron / mil.

The scope includes raw materials, in-bound transport to the Hempel factory, Hempel manufacturing processes, and any Volatile Organic Compounds emitted during and after the application of the product.

It is calculated based on the standard shade defined in this PDS. Values may vary with shade.

# Additional documents

Additional information is available at the Hempel website https://www.hempel.com/service-and-support/technical-guidelines or at your local Hempel website:

- Explanatory Notes for Product Data Sheet.
- Application methods.
- General Application Guidelines

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at <a href="https://www.hempel.com">www.hempel.com</a> (the "Additional documents"):

No	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at www.hempel.com and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at www.hempel.com
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at www.hempel.com

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from www.hempel.com.

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.

hempel.com Issued by Hempel A/S - October 2025