

# System 6

Other metals when painting is required

## System 6A: Stainless steel and aluminium

Pre-qualification is not required

Product	DFT (µm)
Hempadur 15570 or 15590	50
Hempaprime Multi 500	100
Hempel's Pro Acrylic 55883 <sup>2</sup>	75
<b>Total</b>	<b>225</b>

Sweep blasting

## System 6B: Hot dip galvanized steel

Pre-qualification is not required

Product	DFT (µm)
Hempadur 15553	50
Hempaprime Multi 500	100
Hempel's Pro Acrylic 55883 <sup>2</sup>	75
<b>Total</b>	<b>225</b>

No sweep blasting

For advice on regional product availability and additional schemes, please contact your local Hempel representative or email [protective@hempel.com](mailto:protective@hempel.com)

## System 6C: Insulated stainless steel piping and vessels at temperatures < 150°C

Pre-qualification is not required

Product	DFT (µm)
Hempadur 85671	125
Hempadur 85671	125
<b>Total</b>	<b>250</b>

Sweep blasting

Note 1: As pre-qualification is not required additional systems may also be recommended. Contact your Hempel representative for further details. This note applies to all of the above systems.

Note 2: Topcoats which have been pre-qualified in System 1 may also be used for Systems 6A and 6B. Commonly used topcoats, which may be substituted for those listed, include:

- Hempaxane Light 55030
- Hempathane HS 55610
- Hempathane 55210
- Hempathane Speed-Dry Topcoat 250

### Hempel A/S

Lundtoftegaardsvej 91, 2800 Kgs. Lyngby, Denmark  
Tel: +45 4593 3800 Email: [norsok@hempel.com](mailto:norsok@hempel.com)

[norsok.hempel.com](http://norsok.hempel.com)